

p.IVA 00736390964 Cod.Fisc. 02639210158 c.c.i.a. Milano n. 927455 Codice APP/ISS azienda 00736390964

Gammacolor s.r.l. Via Zeuner,5 20822 Seveso (MB) Italy tel. +39 0362550550 fax +39 0362551915 email info@gammacolorsrl.com

Sistema di gestione qualità certificato secondo la UNI EN ISO 9001:2015 da Certiquality.



EGALTEX P

Levelling agent, retarder in dyeing with vat dyes and direct dyes. Suitable for printing for half-tone effects under prints with vat dyes and discharge treatments.

Chemical features: basic oligomer condensation product.

Appearance: amber liquid, slightly viscous

Ionic charge: not ionogen

pH sol. 1:10: sup. to 8

Solubility: it can be diluted in any proportion in cold purified water

Compatibility: it is compatible with surfactants of any ionic charge

Stability: resistant to acids, alkalis and electrolytes at the usual doses of use in the textile field

Foaming power: none

Addition to baths: added to treatment baths only after alkali

Doses of use: as a levelling agent in vat dyeing, it depends on the concentration of dye and on the affinity, like leuco, on the fiber. On average it is used:

from 0.5 to 1 g / l of Egaltex P for a l.r.. = 1:10 and in proportion for others l.r.. For practically difficult dyes and for high affinity fibers, the dose increases up to 1.5-2 g / l Egaltex P is also used to fix bad levelled dyeing.

In the blind vat bath it's employed from 1 to 2 g / 1.

Egaltex P is not used with dyes of the IK method nor with dyes of Indigoide nature.

As a levelling agent in dyeing with Direct dyes it is used from 0.3 to 0.5 gr / 1.

In printing = from 50 to 100 gr / kg of printing paste, for the half-dyed effects, especially under vat prints.

The data reported are the result of accurate studies and / or experience, however, must be considered indicative and in any case without warranty on our part for use. The data contained in this sheet are not to be considered specific.

For information: e-mail info@gammacolorsrl.com