



Gammacolor s.r.l.
Via Zeuner,5 20822 Seveso (MB) Italy
tel. +39 0362550550 fax +39 0362551915
email info@gammacolorsrl.com

Sistema di gestione qualità
certificato secondo la UNI EN ISO
9001:2015 da Certiquality.

p.IVA 00736390964
Cod.Fisc. 02639210158
c.c.i.a. Milano n. 927455
Codice APP/ISS azienda 00736390964



Associazione Tessile e Salute
Azienda associata

GAMMABLANK BVA LIQ.

APPLICATIONS

GAMMABLANK BVA LIQ. is particularly suitable for an exhaust procedure . Is usually employed in the bleaching with hydrogen peroxide at high temperature. And ' suitable for bleaching of staple fibers of viscose in bathrooms brightening and bleaching of mercerized cotton . Can be used in the bleaching of the polyamide with reducing agents and buffering the pH with sodium acetate . It has good lightfastness and excellent fastness to washing . It gives very brilliant shades of white with reflections neutral .

DOSAGE

Exhausting:
0.15-0.60 % for cotton
0.50 to 1.20% for nylon

PROPERTIES

Appearance: amber liquid
Chemical Nature: derived stilbenic
Specific gravity at 20 ° C: 1.12 to 1.15
Ionic charge : Anionic
pH sol. 10% : 9.0
Appearance of aqueous solutions : yellowish clear liquid
Stability to hard water : Up to 15 DH
Stability to pH changes : Stable from 6 to 14
Compatibility: Compatible with anionic and auxiliary products ; incompatible with cationic
Storage stability : Good in normal environmental conditions at temperatures below 5°C can crystallize or thicken without, however, be altered .

The information contained in this circular is indicative in nature . Please adapt the recommendations for



Gammacolor s.r.l.
Via Zeuner,5 20822 Seveso (MB) Italy
tel. +39 0362550550 fax +39 0362551915
email info@gammacolorsrl.com

Sistema di gestione qualità
certificato secondo la UNI EN ISO
9001:2015 da Certiquality.

p.IVA 00736390964
Cod.Fisc. 02639210158
c.c.i.a. Milano n. 927455
Codice APP/ISS azienda 00736390964



Associazione Tessile e Salute
Azienda associata

the use of our products to environmental conditions and materials to be treated .
For more information: e-mail info@gammacolorsrl.com