



Gammacolor s.r.l.
Via Zeuner,5 20822 Seveso (MB) Italy
tel. +39 0362550550 fax +39 0362551915
email info@gammacolorsrl.com

Sistema di gestione qualità
certificato secondo la UNI EN ISO
9001:2015 da Certiquality.

p.IVA 00736390964
Cod.Fisc. 02639210158
c.c.i.a. Milano n. 927455
Codice APP/ISS azienda 00736390964



Associazione Tessile e Salute
Azienda associata

COLDFIX PD

Mixture of alkaly without Silicate, for pad-batch dyeing

Application: pad temperature and fixing (batch): 20-25°C

Dose: from 20 to 100 cc/l on Xg/l dye (100%based)

We suggest to perform a selction of vinylsulphonic reactive dyes to choose those one suitable to cold pad batch method.

g/l dye (100% based)	COLDFIX PD g/l	g/l dye (100% based)	COLDFIX PD g/l	g/l dye (100% based)	COLDFIX PD g/l	g/l dye (100% based)	COLDFIX PD g/l
1	21	32	34	63	47	94	59,5
2	21	33	34	64	47	95	60
3	22	34	34,5	65	47,5	96	60
4	22	35	35	66	48	97	60,5
5	23	36	35	67	48	98	61
6	23	37	36	68	48,5	99	61
7	23,5	38	36	69	49	100	62
8	24	39	36,5	70	49	101	62
9	24	40	37	71	50	102	63
10	24,5	41	37,5	72	50	103	63
11	25	42	38	73	51	104	63,5
12	25	43	38	74	51	105	64
13	26	44	39	75	52	106	64
14	26	45	39	76	52	107	65
15	27	46	39,5	77	52,5	108	65
16	27	47	40	78	53	109	66
17	27,5	48	40	79	53	110	66
18	28	49	40,5	80	54	111	67
19	28	50	41	81	54	112	67
20	29	51	42	82	54,5	113	67,5
21	29	52	42	83	55	114	68
22	30	53	43	84	55	115	68
23	30	54	43	85	56	116	69
24	30,5	55	43,5	86	56	117	69
25	31	56	44	87	57	118	69,5
26	31	57	44	88	57	119	70
27	32	58	45	89	57,5	120	70
28	32	59	45	90	58		
29	32,5	60	46	91	58,5		
30	33	61	46	92	59		
31	33	62	47	93	59		



Gammacolor s.r.l.
Via Zeuner,5 20822 Seveso (MB) Italy
tel. +39 0362550550 fax +39 0362551915
email info@gammacolorsrl.com

Sistema di gestione qualità
certificato secondo la UNI EN ISO
9001:2015 da Certiquality.

p.IVA 00736390964
Cod.Fisc. 02639210158
c.c.i.a. Milano n. 927455
Codice APP/ISS azienda 00736390964



Associazione Tessile e Salute
Azienda associata

- High concentrated liquid
- No silicate content
- Easy to remove with washing
- Chemically stable
- Does not crystallize during pad batch even at 0°C
- Does not penetrate into pad rubber



Gammacolor s.r.l.
Via Zeuner,5 20822 Seveso (MB) Italy
tel. +39 0362550550 fax +39 0362551915
email info@gammacolorsrl.com

**Sistema di gestione qualità
certificato secondo la UNI EN ISO
9001:2015 da Certiquality.**

p.IVA 00736390964
Cod.Fisc. 02639210158
c.c.i.a. Milano n. 927455
Codice APP/ISS azienda 00736390964



Associazione Tessile e Salute
Azienda associata

The information contained in this circular are given according to our best knowledge and experience, however, given the multiplicity of systems of work and applications we can not assume guarantees for the individual case
For information: e-mail info@gammacolorsrl.com